

### Technical Information

Opacity	100% Blackout
Construction	4-Ply Laminated Fiberglass (3 Ply PVC, 1 Ply Fiberglass)
Adhesion	PVC Films Inseparable
Weight	12 oz. per square yard
Breaking Strength	Warp 240 / Fill 960 LBS
Tear Strength	Warp 1700 / Fill 1800 GRAMS
Fire Resistance	U.S. Federal Gvmt Specs CCC-C0521E National Fire Protection Association (NFPA) No. 701 Small Scale Test Boston Fire Dept. BFD 1X-1 California Fire Marshall, Section 13115
Health / Safety	SGS U.S. Testing Company Inc: ISO 22196 Antibacterial Certified
Cleaning	Material can be washed on both sides using warm water and a mild 5% detergent solution



black out



wipe clean only



particularly suitable  
for damp conditions



flame retardant

