



KOPER.<sup>®</sup>

**SMART**

COLLECTION

[www.kopershades.com](http://www.kopershades.com)



## KOPER.

Composition	100% Polyester
Width	300cm
Weight	428 g/m <sup>2</sup> ± 5%
Thickness	0.74 mm ± 5%
Color Fastness	6-7 Grade
Shading Effect	100%Blackout



**G100**



# KOPER.

Composition	100% Polyester
Width	300cm
Weight	400 g/m <sup>2</sup> ± 5%
Thickness	0.60 mm ± 5%
Color Fastness	6-7 Grade
Shading Effect	Blackout





## KOPER.

Composition	100% Polyester
Width	300cm
Weight	330 g/m <sup>2</sup> ± 5%
Thickness	0.50 mm ± 5%
Color Fastness	6-7 Grade
Shading Effect	Blackout



**SHANTUNG1900**



## KOPER.

Composition	100% Polyester
Width	300cm
Weight	330 g/m <sup>2</sup> ± 5%
Thickness	0.50 mm ± 5%
Color Fastness	6-7 Grade
Shading Effect	Blackout



DA



## KOPER.

Composition	100% Polyester
Width	300cm
Weight	364 g/m <sup>2</sup> ± 5%
Thickness	0.53 mm ± 5%
Color Fastness	6-7 Grade
Shading Effect	Blackout



ME




## KOPER.

Composition	40% PVC + 60% Polyester
Width	200 ( customized ) /250/300cm
Weight	440 g/m <sup>2</sup> ± 5%
Openness factor	4%
Thickness	0.45mm ± 5%
Color Fastness	8 Grade
Tensile strength	Warp 3200N/5cm Weft 2000N/5cm
Tear strength	Warp 500N/5cm Weft 220N/5cm



**Y400**



## KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300cm
Weight	390 g/m <sup>2</sup> ± 5%
Openness factor	4%
Thickness	0.66mm ± 5%
Color Fastness	8 Grade
Yarn Count	50*40
Breaking strength	Warp 1450N/5cm Weft 970N/5cm



**D400**



# KOPER.

Composition	30% Polyester + 70% PVC
Width	250/300cm
Weight	434 g/m <sup>2</sup> ± 5%
Openness factor	5%
Thickness	0.67mm ± 5%
Color Fastness	8 Grade
Yarn Count	48*46
Breaking strength	Warp 1310N/5cm Weft 1420N/5cm



**L500**



# KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300cm
Weight	437 g/m <sup>2</sup> ± 5%
Openness factor	3%
Thickness	0.66mm ± 5%
Color Fastness	8 Grade
Yarn Count	50*48
Breaking strength	Warp 1620N/5cm Weft 1600N/5cm



**A300**



# KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300/350cm
Weight	610 g/m <sup>2</sup> ± 5%
Openness factor	0%
Thickness	0.82mm ± 5%
Color Fastness	8 Grade
Yarn Count	60*42
Breaking strength	Warp 3840N/5cm Weft 990N/5cm



**SC**



## KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300/350cm
Weight	514 g/m <sup>2</sup> ± 5%
Openness factor	5%
Thickness	0.74mm ± 5%
Color Fastness	8 Grade
Yarn Count	36*36
Breaking strength	Warp 2233N/5cm Weft 2231N/5cm



**A500**



# KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300/350cm
Weight	410 g/m <sup>2</sup> ± 5%
Openness factor	5%
Thickness	0.55mm ± 5%
Color Fastness	8 Grade
Yarn Count	48*46
Breaking strength	Warp 1600N/5cm Weft 1500N/5cm



**B500**



## KOPER.

Composition	30% Polyester + 70% PVC
Width	200/250/300/350cm
Weight	440 g/m <sup>2</sup> ± 5%
Openness factor	3%
Thickness	0.65mm ± 5%
Color Fastness	8 Grade
Yarn Count	54*44
Breaking strength	Warp 1800N/5cm Weft 1434N/5cm



ALU

KOPER.®

[www.kopershades.com](http://www.kopershades.com)